

Classification

HS221
S221
SW221

Chemical Composition: %

Cu	Sn	Si	Zn	Other
60	1.0	0.3	Balance	0.5

Mechanical and physical properties

Working temperature: 900 °C
Melting range: 875 - 890 °C
Density: 8.4 g/cm³
Tensile strength: 350 N/mm²
Elongation: 35 %
Hardness: about 110 BHN

Joining process

Acetylene torch, induction and resistance heating

Description and Applications

Brazing alloy with good flowing properties, hardly sensitive to overheating. Suitable for gap brazing and coating of steel, cast iron, malleable cast iron, nickel and nickel alloys as well as copper and copper alloys with a solidus of > 900 °C.

Availability

Rods: ϕ 1.5-5.0mm Length: 1000mm
Wire: ϕ 0.8, 1.0, 1.2, 1.6mm on spools D300
Other dimensions are available upon request

BEIDUO ALLOYS

#2999 Binhong West Road, Jinhua , Zhejiang, China
Tel: 86-579-83533866 Mob.:86-13806785765
Email: info@jhbeiduo.com www.beiduoalloys.com