

Classification

Silver Flux QJ305

Chemical Composition:

KF、KBF₄、B₂O₃、Fluoroborate compound

Physical properties

Working temperature: 600-850 °C

Description and Applications

QJ305 Silver flux paste more permeable than ordinary silver brazing agent, good diffuse flow, easy to use, in the range of 600-850 degrees Celsius can effectively cooperate with the silver base, copper base brazing material and copper, steel, stainless steel, high temperature alloy welding, especially suitable for hard alloy, diamond welding

Packing:

250g/bottle, 500g/bottle

BEIDUO ALLOYS

#2999 Binhong West Road, Jinhua , Zhejiang, China

Tel: 86-579-83533866 Mob.:86-13806785765

Email: info@jhbeiduo.com www.beiduoalloys.com