

TECHNICAL SHEET

Brass Brazing Alloy

BEIDUO® Alloys

Providing Complete Brazing, Soldering & Welding

000001

Classification

AWS A5.8: RBCuZn-A
EN ISO 3677: B-Cu60Zn(Si)-875/895
DIN 8513: L-CuZn40
DIN EN1044: CU 301
ISO 17672: Cu 470a

Chemical Composition: %

Cu	Sn	Si	Zn	Other
60	<0.6	<0.05	Balance	0.5

Mechanical and physical properties

Working temperature: 900 °C
Melting range: 875 - 890 °C
Density: 8.4 g/cm³
Tensile strength: 350 N/mm²
Elongation: 35 %
Hardness: about 110 BHN

Joining process

Acetylene torch, induction and resistance heating

Description and Applications

Brazing alloy with good flowing properties, hardly sensitive to overheating. Suitable for gap brazing and coating of steel, cast iron, malleable cast iron, nickel and nickel alloys as well as copper and copper alloys with a solidus of > 900 °C.

Availability

Rods: ϕ 1.5-5.0mm Length: 1000mm
Wire: ϕ 0.8, 1.0, 1.2, 1.6mm on spools D300
Other dimensions are available upon request

BEIDUO ALLOYS

#2999 Binhong West Road, Jinhua , Zhejiang, China

Tel: 86-579-83533866 Mob.:86-13806785765

Email: info@jhbeiduo.com www.beiduoalloys.com